



Technical documents of glued steel fiber -SD65/60G

Product Model	SD65/60G (3D)
Aspect Ratio (L/D)	65
Length (mm)	60±2
Diameter (mm)	0.90±0.02
Shape	Hooked End
Tensile Strength (MPa)	≥1100/1800/2300
Number of Fibers per kg	3900
Certification Standard	EN 14889-1, ASTM A820/A820M
Packaging Specification	20kg/bag/case; 1200kg/pallet, 1300kg/pallet
Application Scenarios	Airport warehouse, cold storage, heavy-duty floor
Project Cases	Zhejiang industrial floor ,Weihai Warehouse
Product Features	<ol style="list-style-type: none">1. Water-soluble adhesive technology, rapid dispersion within 30 seconds of stirring, no agglomeration;2. Dual-end hook structure enhances anchoring strength and energy absorption;3. Forms a three-dimensional reinforcement network in concrete, significantly improving crack resistance, impact resistance, and fatigue resistance;4. Easy application with direct feeding or pumping, suitable for large-area pouring
Technical and Engineering Support	<ol style="list-style-type: none">1. Professional project specification formulation;2. fiber type & dosage optimization;3. concrete mix design improvement;4. performance test supervision;5. on-site construction guidance;6. dosing equipment installation & debugging;7. one-stop technical support from planning to completion
Safety and Storage	<ol style="list-style-type: none">1. Wear head, eye protection and gloves during operation;2. Store in a dry and ventilated place;3. Avoid heavy stacking;4. Prevent moisture and corrosion